E-ISSN: 2997-9382
American Journal of Technology Advancement
https://semantjournals.org/index.php/AJTA

| Research Article

Check for updates

High-Strength Concrete Cover Requirements for Foundations in Aggressive Soil

Prof. Dr. Hussam Ali Mohammed, Hanan Riyadh Muhsen
Technical College of Al-Mussaib, Al-Furat Al-Awsat Technical University

Annotation

Concrete cover must be utilized in excess of the prescriptive minimums in order to ensure the durability of foundations in aggressive soils. In this review, a performance-based method is developed to select and verify cover for high-strength concrete (HSC) foundations. This is done in recognition of the fact that durability necessitates the material characteristics that are typically associated with high-performance concrete (HPC), such as a low water-to-binder ratio, optimized supplementary cementitious materials (SCMs), and efficient curing. Our process involves the synthesis of degradation mechanisms, such as sulfate attack, chloride ingress, and carbonation. Additionally, we quantify the links between transport and life, and we align the detailing (cover, crack control, execution tolerances) with ACI 318, EN 206/EC2, and fib service-life frameworks. We demonstrate the circumstances and reasons behind the need for earth-contact increases that exceed the ACI minimum of 75 millimeters (typically 90–100 millimeters for severe XS/XD/XA exposures or a design life of at least 75 years). Additionally, we demonstrate how to strike a balance between cover and mix quality through probabilistic verification, such as LIFE-365 and DuraCrete. Furthermore, we demonstrate which compensatory measures (inhibitors, surface protection, and non-corroding reinforcement) are most effective when geometry is a constraint on cover. A reasonable and lifecycle-optimized specification for HSC foundations in aggressive soils has been produced as a result of this initiative.

Keywords: High-strength concrete; Aggressive soils; Concrete cover; Service-life prediction; Reliability-based design.

This is an open-access article under the CC-BY 4.0 license

1. Introduction

High-strength concrete (HSC) is defined as concrete with a compressive strength (f'c) equal to or more than 50 MPa. However, durability is not solely determined by strength alone. Therefore, we require that HSC adhere to the HPC-type durability standards throughout the entire process, which include low permeability (low w/b), SCMs, and stringent curing [8–11].

The distance from the surface to the nearest reinforcing steel is the distance that constitutes the concrete cover. When it comes to EC2, the nominal cover, denoted as c_nom, is calculated by

adding the minimum cover for exposure to the execution deviation allowance, denoted as Δc_dev [2–3]. It is required by ACI 318-19 that elements that are cast against and permanently exposed to soil have a minimum cover of at least 75 millimeters [1]. There are a number of different exposure classifications that map to chloride (XS/XD; ACI corrosion exposure), sulfate (XA; ACI S exposure), and other substances (the danger of carbonation is exacerbated on dry–wet cycles) [1–3, 6, 12].

2. Degradation mechanisms under aggressive soils

2.1 Sulfate attack :

The cover experiences expansion, microcracking, and a loss of stiffness as a result of the reaction between external sulfates and aluminates, which results in the formation of ettringite/thaumasite. Low-C3A binders, SCMs (slag/fly ash), reduced permeability, and appropriate curing are some of the mitigation strategies discussed in [6, 9, 13–14]. The EN 206/EC2 and ACI durability guides both include provisions for the classification of severity and the requirements for the binder.[2–3, 6].

2.2 Chloride-induced corrosion :

As a result of sorption and diffusion, chlorides made their way through the cover. There are two phases that make up service life: initiation, which is the period of time until the chloride concentration at bar depth reaches C_crit and steel depassivates, and propagation, which is the growth of cracks and spalls. Extending the initiation time and decreasing the propagation rates can be accomplished by increasing cover, decreasing D_app, limiting surface concentration Cs, and constraining crack width simultaneously [7, 9, 11–12, 17–20, 24].

2.3 Carbonation :

Upon reaching reinforcement, the carbonation front neutralizes alkalinity, resulting in a decrease in pH from more than 12.5 to around 9. This process depassivates steel without the presence of chlorides. Low permeability and prolonged moist curing are two methods that can be used to mitigate the risks that are associated with under-cured SCM-rich mixtures and dry–wet cycling. [9–10, 12, 15, 32].

3. Transport parameters and service-life relations

For chlorides, a semi-infinite Fickian solution gives: C(x,t) = Cs · erfc[x / (2·sqrt(D_app·t))]. A practical initiation-time estimate is: t_i ≈ (c_cover^2) / (4·D_app) · [erfc^-1(C_crit/Cs)]^-2, with D_app(t) = D_ref · (t/t_ref)^(-m) to represent aging/continued hydration. Carbonation depth often follows x_c = k_c·sqrt(t) ⇒ t_c = (c_cover / k_c)^2 under quasi-steady conditions [15–19]. Apparent diffusion is temperature- and moisture-dependent (Arrhenius-type scaling) [18–19].

Testing to characterize transport: bulk diffusion (ASTM C1556; NT Build 443), migration (NT Build 492), RCPT screening (ASTM C1202), sorptivity (ASTM C1585), carbonation depth (RILEM CPC-18). Always specify age, curing, and temperature for comparability [21–25, 29, 31].

4. HSC mixes for durability (HPC criteria within HSC)

Durability-grade HSC should satisfy: (i) Low w/b (≤ 0.40) with HRWR to reduce connected capillary porosity [8–11]; (ii) SCMs: 5–10% silica fume for chloride resistance; 30–65% slag or suitable fly ash for sulfate mitigation and pore refinement; tailor to exposure and curing [9–10, 12–14]; (iii) Curing: continuous moist curing ≥ 7–14 days for SCM-rich mixes; inadequate curing negates diffusion/carbonation benefits [9–10, 12, 15]. Trade-offs: SCMs lower D_app and improve sulfate resistance but can raise carbonation susceptibility if under-cured; specifications must therefore couple mix, curing, and cover [9–10, 12, 15].

5. Cover selection: prescriptive minima vs performance verification

Prescriptive baseline — ACI 318-19: ≥ 75 mm minimum cover for concrete cast against and permanently exposed to earth [1]. EC2/EN 206: determine c_min by exposure class (XD/XS/XA) and add Δc_dev (execution tolerance) to obtain c_nom [2–3].

When to increase cover : Increase nominal cover to 90–100 mm when any of the following apply:

(i) XS/XD severe exposures (marine splash/tidal; heavy de-icing), (ii) XA high sulfate/activity,

(iii) design life ≥ 75–100 years, (iv) limited access for maintenance, (v) expected crack widths are tightly controlled by detailing [2–5, 12, 17–20, 27].

Balancing cover and material quality : Use service-life modeling to choose the least-cost combination meeting target reliability (beta). Larger cover reduces ingress but may elevate crack risk and rebar congestion; reducing D_app via SCMs achieves similar reliability with thinner cover—provided curing and carbonation are addressed [4–5, 17–20, 24, 27].

6. Crack control and execution tolerances

Crack width limits: adopt wk ≤ 0.2–0.3 mm for XS/XD practice; tighter limits for severe marine splashes. Control via bar spacing/diameter, restraint management, and service stress limits [1–2, 20]. Execution: specify and verify cover using spacers, bar supports, and covermeters/GPR; include Δc_dev explicitly (EC2) and ACI tolerances (ACI 117) in the spec [2–3, 30].

7. Models, tools, and probabilistic verification

Chlorides: LIFE-365 operationalizes Fickian initiation-time with aging, temperature, and mix libraries; calibrate with project diffusion/migration tests [17–18]. Probabilistic design: DuraCrete treats c_cover, D_app, Cs, C_crit and workmanship as random variables; compute beta for initiation limit state at design life T_d. Typical targets beta ≈ 1.3 (illustrative) for 50 years; adjust with asset criticality [19]. Carbonation: calibrate k_c to mix/curing and ambient CO2/RH; consider coupled moisture effects [15–16].

8. Acceptance testing and QA/QC

Prequalification: specify thresholds for D_app (C1556/NT443) at stated age/curing; migration (NT492) for ranking; RCPT (C1202) as a screening surrogate with correlation to diffusion; sorptivity (C1585) and carbonation (CPC-18) as needed [21–25, 29, 31]. Curing control: continuous moist curing records; temperature/humidity logs; verify curing before demolding/sealing [9–10, 12]. As-built: cover surveys, crack width measurements, joints/sealants compliance; EN 13670 execution checks; ACI 117 tolerances [2–3, 28, 30].

9. Practical decision aids

Table 1. Indicative nominal cover ranges by exposure class (sources: [1–3]).

Exposure (EC2/ACI)	Soil/groundwater condition	Typical c_nom	Notes
Exposure (EC2/ACI)	Soil/groundwater condition	Typical c_nom	Notes
Moderate chlorides (XD1/XS1)	Low to moderate salinity; limited splash	75–90 mm	Verify D_app and crack control
Severe chlorides (XD3/XS3)	Splash/tidal; heavy de-icing	90–100 mm	Prefer slag/silica fume; strict curing
High sulfates (XA2–XA3)	SO4^2- above class limits	90–100 mm	Low-C3A/slag binders; verify

			expansion risk
Carbonation-sensitive	Dry–wet cycles; SCM-rich mixes	85–95 mm	Extend moist curing; verify k_c

Note: Values are indicative; final cover should be verified by life modeling and probabilistic checks.

If cover is constrained: (i) reduce D_app via SCM-rich HSC and curing; (ii) apply EN 1504-2 surface protections; (iii) specify epoxy-coated/stainless/FRP reinforcement in critical zones; (iv) use inhibitors (ASTM C1582) with documented performance [12, 18, 26–27, 33–35].



Figure 1. Time-to-initiation vs. cover (Base mix). After [17–19].



Figure 2. Time-to-initiation vs. cover (Improved mix, D_ref halved). After [17–19].



Figure 3. Time-to-initiation vs. cover (Lower surface chloride C_s = 0.60%). After [17–19].



Figure 4. Sensitivity of t_i to D_ref (log scale). After [17–19].



Figure 5. Carbonation time vs. cover for different k_c values. After [15].

Table 2. Worked example results across covers and scenarios (sources: [17–19]).

Cover (mm)	t_i Base (years)	t_i Improved mix (years)	t_i Lower C_s (years)	Comment
65	48.7	153.5	67.9	Higher cover → longer t_i
75	78.2	246.9	109.0	Higher cover → longer t_i
85	118.4	374.2	165.1	Higher cover → longer t_i
100	203.0	642.6	283.4	Higher cover → longer t_i
120	372.1	1178.9	519.6	Higher cover → longer t_i

Table 3. Testing and acceptance methods for transport properties (sources: [21–25, 29, 31]).

Property	Method/Standard	Use in spec	Notes
Apparent chloride diffusion	ASTM C1556; NT Build 443	Acceptance (thresholds at age/curing)	Project-specific calibration
Migration coefficient	NT Build 492	Screening/ranking	Correlate to diffusion via project curve
Electrical charge passed	ASTM C1202 (RCPT)	Screening only	Beware ionic/electrical artifacts
Water absorption	ASTM C1585	Supplementary	Sensitive to curing and surface finish
Carbonation depth	RILEM CPC-18	Diagnostic/qualification	Controlled exposure regime

Table 4. Typical surface crack-width limits in aggressive exposure (sources: [1–2, 20]).

Exposure	Recommended w_k (mm)	Notes
XS/XD (general)	≤ 0.3	Often adequate with 75–90 mm cover
XS3/XD3 (severe)	≤ 0.2	Prefer 90–100 mm cover; strict detailing
XA (high sulfates)	Serviceability crack limits + binder selection	Limit ingress + sulfate-resistant binder

Table 5. Model input parameters used in sensitivity analyses (sources: [15, 17–19]).

Parameter	Symbol/Unit	Base value	Range (if applicable)	Notes
Reference diffusion (28 d)	D_ref (m^2/s)	3.0×10^{-12}	1.0×10^{-12}–6.0×10^{-12}	Life-365 style; temperature held constant
Aging exponent	m (-)	0.40	0.2–0.6	Project-specific calibration
Surface chloride	C_s (% mass conc.)	0.90%	0.40–1.20%	Driven by exposure &

				covercrete quality
Chloride threshold	C_crit (% mass conc.)	0.05%	0.02–0.10%	Literature spread; steel & concrete dependent
Cover depth	c_cover (mm)	75, 100	65–120	Nominal cover including Δc_dev per EC2

10. Conclusion

For HSC foundations in aggressive soils, the minimum 75 mm cover (ACI 318) is a starting point, not a guarantee of durability. Performance-based selection—raising nominal cover to 90–100 mm where warranted, pairing with low-permeability HSC (HPC criteria), enforcing crack control and curing, and probabilistically verifying service life—delivers robust, economical outcomes. Where geometry limits cover, deploy compensatory measures validated in the life model to meet target reliability .

References

1. ACI Committee 318 (2019). Building Code Requirements for Structural Concrete (ACI 318-19) and Commentary. ACI.
2. CEN (2004). Eurocode 2: Design of Concrete Structures — Part 1-1 (EN 1992-1-1:2004). CEN.
3. CEN (2013). Concrete — Specification, Performance, Production and Conformity (EN 206:2013). CEN.
4. fib (2006). Model Code for Service Life Design (Bulletin 34). fib.
5. fib (2016). Performance-Based Specifications for Concrete (Bulletin 80). fib.
6. ACI Committee 201 (2016). Guide to Durable Concrete (ACI 201.2R-16). ACI.
7. ACI Committee 222 (2011). Guide to Mitigate Corrosion of Steel in Concrete (ACI 222.3R-11). ACI.
8. ACI Committee 363 (2010). Report on High-Performance Concrete (ACI 363R-10). ACI.
9. Mehta, P. K., & Monteiro, P. J. M. (2014). Concrete: Microstructure, Properties, and Materials (4th ed.). McGraw-Hill.
10. Aïtcin, P. C. (1998). High-Performance Concrete. E & FN Spon.
11. Bertolini, L., Elsener, B., Pedeferri, P., & Polder, R. (2013). Corrosion of Steel in Concrete (2nd ed.). Wiley-VCH.
12. Broomfield, J. P. (2019). Corrosion of Steel in Concrete (3rd ed.). CRC Press.
13. Skalny, J., Marchand, J., & Odler, I. (2002). Sulfate Attack in Concrete. Spon Press.
14. Lothenbach, B., Scrivener, K., & Hooton, R. D. (2018). Long-term performance in sulfate-rich environments. Cement and Concrete Research, 114, 1–6.
15. Papadakis, V. G., Vayenas, C. G., & Fardis, M. N. (1991). Modeling of concrete carbonation. ACI Materials Journal, 88(4), 363–373.
16. Tuutti, K. (1982). Corrosion of Steel in Concrete. CBI.
17. Life-365 Consortium (2018). Life-365 Service Life Prediction Model, v2.2.1 — User Manual.

18. Bentz, D. P., & Thomas, M. D. A. (2014). Service Life Prediction of Concrete: The PERD Model. NIST.
19. DuraCrete (2000). Statistical Quantification of Variables in Limit State Functions. Brite EuRam III.
20. O'Reilly, M., & Darwin, D. (2010). Cover and Cracking in Reinforced Concrete: New Provisions in ACI 318-11. Univ. of Kansas.
21. ASTM C1556. Apparent Chloride Diffusion Coefficient by Bulk Diffusion.
22. NT Build 443. Hardened Concrete — Accelerated Chloride Penetration.
23. NT Build 492. Chloride Migration Coefficient from Non-Steady-State Migration Experiments.
24. ASTM C1202. Electrical Indication of Concrete's Ability to Resist Chloride Ion Penetration.
25. ASTM C1585. Rate of Absorption of Water by Hydraulic-Cement Concretes.
26. ASTM C1582/C1582M. Admixtures to Inhibit Chloride-Induced Corrosion of Steel in Concrete.
27. ACI Committee 222 (2019). Protection of Metals in Concrete Against Corrosion (ACI 222R-19). ACI.
28. CEN EN 13670. Execution of Concrete Structures.
29. RILEM CPC-18 (1988). Measurement of Hardened Concrete Carbonation Depth.
30. ACI Committee 117 (2010). Tolerances for Concrete Construction and Materials (ACI 117-10). ACI.
31. Tang, L., & Nilsson, L.-O. (1992). Rapid chloride diffusivity under electrical field. ACI Materials Journal, 89(1), 49–53.
32. Neville, A. M. (2011). Properties of Concrete (5th ed.). Pearson.
33. CEN EN 1504-2. Surface Protection Systems for Concrete.
34. fib (2013). fib Model Code for Concrete Structures 2010. fib.
35. Thomas, M. D. A. (1996). Chloride thresholds in concrete—A review. Cement and Concrete Research, 26(7), 1019–1030.
36. Andrade, C., & Alonso, C. (2004). Test methods for on-site corrosion rate measurement. Materials and Structures, 37, 623–643.
37. Beushausen, H., & Alexander, M. (2008). Performance-based durability design. Cement and Concrete Composites, 30(5), 388–397.
38. Thomas, M., Hooton, R. D., Scott, A., & Zibara, H. (2012). The effect of SCMs on chloride binding and diffusion. Cement and Concrete Research, 42(1), 1–7.
39. Fredriksen, J., et al. (2019). Carbonation of concrete with SCMs—state of the art. Materials and Structures, 52, 33.
40. Alexander, M., & Mackechnie, J. (2003). Model for cover cracking due to corrosion of reinforcement. Magazine of Concrete Research, 55(5), 391–401.